

Scheda tecnica Rete elettrosaldata Austria


Technical specification: Standard Welded Meshes Austria

Composizione chimica / Chemical composition					
C % max	P % max	S % max	Cu % max	N % max	Ceq. Max
0.22	0.050	0.050	0.80	0.012	0.50
(0.24)	(0.055)	(0.055)	(0.85)	(0.014)	(0.52)

I valori tra parentesi si applicano per analisi sul prodotto/ *The figures in brackets apply to product analysis*

Proprietà meccaniche – Mechanical properties								
Nazione <i>Nation</i>	Norma <i>Standard</i>	Marca <i>Grade</i>	Re N/mm ²	Rm N/mm ²	Re/Re nom	A 10 %	A 5 %	Agt %
AUSTRIA / AUSTRIA	ONORM 42000/7	M550	≥ 550	≥ 620	≥ 1.05		≥ 8	

Qualifiche / Certifications	
Nazione <i>Country</i>	AUSTRIA / AUSTRIA
Ente Qualificazione <i>Certification body</i>	

Geometria nervature e marchio di laminazione <i>Ribs geometry and rolling mark</i>


RETI ELETTROSALDATE SECONDO ONORM4200/7 / ELEKTROGESCHWEISSTES BAUSTAHLMATTEN GEMASS ONORM 4200/7														
Tipologie <i>Typologie</i>	Ø fili / Ø drahte mm		maglia / masche mm		pannello / paneel mm		sporgenza fili mm <i>worsprung drahte</i> mm		pannelli per pacco <i>paneel</i> pro paket	peso pannello <i>gewicht</i> paneele kg	N. fili pannello <i>R. drahte paneel</i>		Peso fili pannello <i>Gewicht drahte</i> <i>paneel</i> kg	
	Long. <i>Langss.</i>	Trasv. <i>Quer.</i>	Long. <i>Langss.</i>	Trasv. <i>Quer.</i>	Largh. <i>Width.</i>	Lungh. <i>Quer.</i>	Long. <i>Langss.</i>	Trasv. <i>Quer.</i>			Long. <i>Langss.</i>	Trasv. <i>Quer.</i>	Long. <i>Langss.</i>	Trasv. <i>Quer.</i>
AQ 46	4.6	4.6	100	100	2400	6000	50	50	50	37.57	24	60	18.79	18.79
AQ 50	5	5	100	100	2400	6000	50	50	50	44.35	24	60	22.19	22.19
AQ 55	5.5	5.5	100	100	2400	6000	50	50	50	53.86	24	60	26.86	26.86
AQ 60	6	6	100	100	2400	6000	50	50	25	63.94	24	60	31.96	31.96
AQ 65	6.5	6.5	100	100	2400	6000	50	50	25	74.88	24	60	37.44	37.44
AQ 70	7	7	100	100	2400	6000	50	50	25	86.98	24	60	43.49	43.49
AQ 76	7.6	7.6	100	100	2400	6000	50	50	25	102.53	24	60	51.26	51.26
AQ 82	8.2	8.2	100	100	2400	6000	50	50	20	119.52	24	60	59.76	59.76
AQ 90	9	9	100	100	2400	6000	50	50	15	143.71	24	60	71.85	71.85
AQ 100	10	10	100	100	2400	6000	50	50	10	177.70	24	60	88.85	88.85
A 70	7	5.5	100	300	2400	6000	150	50	25	52.46	24	20	43.49	8.95
A 82	8.2	6.5	100	300	2400	6000	150	50	25	72.24	24	20	59.69	12.50

Su richiesta si possono realizzare reti a misura e/o disegno del cliente.
Auf anfrage können wir paneele verschiedener gröÙe.